

Microestil® DECO-PAST



PRODUCT INFORMATION

Micro-mortar in paste to use for the creation of decorative floors and wall tiles. Quick and easy application. Supplied in ready-to-use paste. Without Potlife. High resistance to abrasion. Finishes of high hardness, FINE and EXTRA FINE. Interior Exterior. 48 Microestil color chart.

TECHNICAL DATA OF APPLICATION			
Product description	One-component, ready-to-use paste micromorter, indicated for the creation of continuous decorative floor and wall tiles. Excellent adhesion on concrete, ceramic, marble, plaster, etc., as well as any stable surface.		
Surface preparation	The surface must have a minimum resistance of 1.5 N / mm ² , it must be clean, free of cracks, traces of oil, grease and paints as well as any contaminant that may prevent a correct adhesion to the support. In case of doubt, carry out previous tests. The support must always be prepared by mechanical means such as diamond grinding or milling and subsequent vacuuming of the surface. Due to the low thickness of the coating (2-3mm), higher levels of support leveling are required. Cementitious surfaces and supports of different absorption will be primed or PRIMER P541. If the substrate presents humidity due to groundwater or capillary rise, we recommend not using our system as said humidity would cause its destruction.		
Colour	White		
Conservation	One year from its date of manufacture, in its original container, unopened, indoors and avoiding frost. Do not store directly in the sun.		
Technical data	DECO-PAST BASE	DECO-PAST FINO	DECO-PAST EXTRA FINO
	Mortar for regularization and smoothing of surfaces	Decorative micromorter with high resistance to abrasion	Decorative micromorter for smooth or textured finishes
consumption	0.8-1Kg / m ² / coat	0,4-0,6Kg/m ² /coat	0,25Kg/m ² /coat
Envase	15Kg	15 y 5Kg	15 y 5Kg
Solid content	100%		
Use	Before using DECO-PAST, stir with a mechanical stirrer together with the chosen pigment dose. Apply in a thin layer with a stainless steel or plastic trowel a first layer of DECO-PAST BASE, after 4 to 6 hours depending on the temperature and ambient humidity, sand the surface with 80 or 120 grit sandpaper and then vacuum up the dust. Apply a second coat of DECO-PAST BASE in the same way. After 12 hours apply a first coat of DECO-PAST FINO or EXTRA FINO depending on the type of surface to be coated, after 2 to 4 hours apply a second coat. After a minimum of 12 to 24 hours, sand evenly by mechanical means (orbital sander) and vacuum the surface, then proceed to apply the HIDROLACA + ESTILPUR protective seal.		

Microestil® DECO-PAST



Application conditions	The ambient temperature must be between 10°C and 25°C.
Observations	Due to the granulometric difference between DECO-PAST FINO and EXTRA FINO, at the same dosage of pigment the shade will be slightly different, the shade being the highest in MH. The resulting colors of DECO-PAST EXTRA FINO correspond to the Microestil color chart. Base TR.
Cleaning	After using the tools, they should be cleaned immediately with water.
Cautions	When applying the product, adopt the appropriate individual protection measures for the use indicated in this technical sheet, protect the skin and eyes. In case of contact, rinse with plenty of water. In case of contact with the eyes, also visit a doctor. Once hardened it is harmless. Professional use.

Note: This technical data sheet serves, like all other recommendations and technical information, only to describe the characteristics of the product, how to use it and its applications. The data and information reproduced are based on our technical knowledge obtained in the literature, laboratory tests and in practice. The data on consumption and dosage that appear in this technical sheet are based on our own experience, so these are susceptible to variations due to the different conditions of the works. The actual consumptions and dosages must be determined on site, by means of previous tests and are the responsibility of the client. For additional advice consult our technical service. Microestil Cement, s.l. reserves the right to modify the composition of the products, as long as they continue to fulfill the characteristics described in the technical sheet. Other applications of the product that do not conform to those indicated, will not be our responsibility. We grant a guarantee in the event of manufacturing quality defects of our products, excluding additional claims, being our sole responsibility to re-enter the value of the merchandise supplied. This data sheet loses its validity with the appearance of a new edition.