

HIDROLACA



PRODUCT INFORMATION

Acrylic sealant

DATOS TÉCNICOS DE APLICACIÓN

Area of application	Decoration and protection of continous cementitious pavements, protection of clay and natural stone floors, as a primer before the application of Estilpur varnishes.					
Product description	Acrylic one-component sealant in water base for the protection and sealing of cementitious pavements. Especially recommended for prior application to Estilpur varnishes. Easy horizontal and vertical application. Excellent wetting support. Excellent infiltration and consolidation, blocking any future efflorescence. Good general resistance to chemical spills. Quick dry					
Conservation	Storage into the original package, closed and avoiding direct sunlight. The product has at least 1 year life. Although it does not have dregs at rest, it is essential to shake the product before their application. Product sensitive to freezing.					
Package	<table border="1"> <tr> <td>Pot</td> <td>Pot</td> </tr> <tr> <td>1kg</td> <td>5kg</td> </tr> </table>	Pot	Pot	1kg	5kg	
Pot	Pot					
1kg	5kg					
Approx. consumption	7 - 8 m2 / l depend absorption support.					
Use	<p>Do not apply when there is risk of imminent rain, the minimum temperature application is + 5°C . Do not apply to temperatures above 35°C as drying can be too fast, forming surface defects. As a general rule always apply on ready supports and free powder. Although the product has a dry powder and tact quickly, wait between coats at least 2 hours in summer and 4 hours in winter although this may seem visually dry. short hair roller or microfiber roller</p> <p>The subsequent application of varnish will make passed 12 hours in summer and 24 in winter.</p>					



HIDROLACA



Technical Features	Product: Acrylic resin. Specific weight: 1,017 +/- 0,020 Kg / L Appearance: bright. Weight solid: 30% +/- 2% Combustion point: non-flammable product. Voc`s: 1,1 g/l
Dry	Tact dried: 30 minutes at 20° C and 60% relative humidity. Interval between coats: Minimum 2 hours at 20° C. Maximum does not have
Cleaning	After using the tools should be cleaned immediately with water.
Cautions	Use resistant protective chemicals gloves. Wear safety glasses with side protection (with frame). Wash hands and / or face before breaks and after to finish work .Avoid contact with the eyes and skin. Use personal protection clothes. Consult the Safety Technical Datasheet.

NOTE: this technical datasheet serves as all other recommendations and technical information, is to describe the product characteristics, mode of use and applications. The information supplied is based on our technical knowledge obtained in the bibliography, laboratory tests and in practice. The data about consumption and dosage contained in this datasheet is based upon extensive experience so these are susceptible to variations due to the different conditions of work. Real consumption and dosages should be decided on -site through preliminary tests and are the responsibility of the customer. For further advice contact our technical service. Microestil Cement, SL reserves the right to update and change the composition of the products. Other product applications that do not conform to those indicated will not be our responsibility. We give guarantee in case of manufacturing defects quality of our products, excluding any other complaints, only to be our responsibility to return the value of the goods supplied. The present technical datasheet loses your validity with the appearance of a new edition.